

norm

NEN-EN 10025-3

Hot rolled products of structural steels -
Part 3: Technical delivery conditions for
normalized/normalized rolled weldable
fine grain structural steels

Publicatie uitsluitend voor commentaar

april 2011
ICS 77.140.10; 77.140.50

Commentaar vóór 2011-07-17

Zal vervangen NEN-EN 10025-3:2004

Als Europees normontwerp is gepubliceerd: prEN 10025-3:2011, IDT

Definitief vastgestelde normen zullen als Nederlandse norm gelden. Daarom wordt dit normontwerp in Nederland voor commentaar gepubliceerd. Op het ontwerp ingebracht commentaar zal aan de bevoegde normcommissie worden voorgelegd die hiermee rekening zal houden bij de bepaling van de Nederlandse stem. Indien er geen bezwaar bij NEN wordt gebracht, kan dat leiden tot ongewijzigde definitieve vaststelling van het ontwerp als norm.

Van Europese normen bestaan drie officiële versies: Engels, Frans en Duits. Voor Nederland zal de Engelse versie gelden. Daarnaast kan er gekozen worden voor een andere geautoriseerde versie in het Nederlands.

Normcommissie 342081 "Constructiestaal"

Apart from exceptions provided by the law, nothing from this publication may be duplicated and/or published by means of photocopy, microfilm, storage in computer files or otherwise, which also applies to full or partial processing, without the written consent of the Netherlands Standardization Institute.

The Netherlands Standardization Institute shall, with the exclusion of any other beneficiary, collect payments owed by third parties for duplication and/or act in and out of law, where this authority is not transferred or falls by right to the Reproduction Rights Foundation.

Auteursrecht voorbehouden. Behoudens uitzondering door de wet gesteld mag zonder schriftelijke toestemming van het Nederlands Normalisatie-instituut niets uit deze uitgave worden verveelvoudigd en/of openbaar gemaakt door middel van fotokopie, microfilm, opslag in computerbestanden of anderszins, hetgeen ook van toepassing is op gehele of gedeeltelijke bewerking.

Het Nederlands Normalisatie-instituut is met uitsluiting van ieder ander gerechtigd de door derden verschuldigde vergoedingen voor verveelvoudiging te innen en/of daartoe in en buiten rechte op te treden, voor zover deze bevoegdheid niet is overgedragen c.q. rechtens toekomt aan de Stichting Reprorecht.

Although the utmost care has been taken with this publication, errors and omissions cannot be entirely excluded. The Netherlands Standardization Institute and/or the members of the committees therefore accept no liability, not even for direct or indirect damage, occurring due to or in relation with the application of publications issued by the Netherlands Standardization Institute.

Hoewel bij deze uitgave de uiterste zorg is nagestreefd, kunnen fouten en onvolledigheden niet geheel worden uitgesloten. Het Nederlands Normalisatie-instituut en/of de leden van de commissies aanvaarden derhalve geen enkele aansprakelijkheid, ook niet voor directe of indirecte schade, ontstaan door of verband houdend met toepassing van door het Nederlands Normalisatie-instituut gepubliceerde uitgaven.

Voorbeeld
Preview

March 2011

ICS 77.140.10; 77.140.50

Will supersede EN 10025-3:2004

English Version

Hot rolled products of structural steels - Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels

Produits laminés à chaud en aciers de construction - Partie 3: Conditions techniques de livraison pour les aciers de construction soudable à grains fins à l'état normalisé/laminage normalisé

Warmgewalzte Erzeugnisse aus Baustählen - Teil 3: Technische Lieferbedingungen für normalgeglühte/normalisierend gewalzte schweißgeeignete Feinkornbaustähle

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ECISS/TC 103.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
1 Scope	5
2 Normative references	5
2.1 General standards	5
2.2 Standards on dimensions and tolerances (see 7.7.1).....	6
2.3 Standards on testing	6
3 Terms and definitions	7
4 Classification and designation.....	7
4.1 Classification.....	7
4.1.1 Main quality classes	7
4.1.2 Grades and qualities	7
4.2 Designation	7
5 Information to be supplied by the purchaser	8
5.1 Mandatory information	8
5.2 Options	8
6 Manufacturing process	8
6.1 Steel making process.....	8
6.2 Grain structure	8
6.3 Delivery conditions.....	8
7 Requirements	9
7.1 General.....	9
7.2 Chemical composition	9
7.3 Mechanical properties.....	9
7.3.1 General.....	9
7.3.2 Impact properties.....	10
7.3.3 Improved deformation properties perpendicular to the surface	10
7.4 Technological properties	10
7.4.1 Weldability	10
7.4.2 Formability and flame straightening.....	10
7.4.3 Suitability for hot-dip zinc-coating.....	11
7.5 Surface properties	11
7.5.1 Strip	11
7.5.2 Plates and wide flats	12
7.5.3 Sections	12
7.5.4 Bars and rods.....	12
7.6 Internal soundness	12
7.7 Dimensions, tolerances on dimensions and shape, mass.....	12
8 Inspection	12
8.1 General.....	12
8.2 Type of inspection and inspection document	13
8.3 Frequency of testing	13
8.3.1 Sampling.....	13
8.3.2 Test units	13
8.3.3 Verification of chemical composition.....	13
8.4 Tests to be carried out for specific inspection.....	13
9 Preparation of samples and test pieces.....	14
9.1 Selection and preparation of samples for chemical analysis	14

9.2	Location and orientation of samples and test pieces for mechanical tests	14
9.2.1	General	14
9.2.2	Preparation of samples.....	14
9.2.3	Preparation of test pieces.....	14
9.2.4	Impact test pieces	14
9.3	Identification of samples and test pieces	14
10	Test methods	14
10.1	Chemical analysis	14
10.2	Mechanical tests.....	14
10.3	Ultrasonic testing	15
10.4	Retests.....	15
11	Marking, labelling, packaging	15
12	Complaints	15
13	Options (see 5.2).....	15
Annex A (informative)	List of corresponding former designations	22
Bibliography		23

Copyright
Preview

Foreword

This document (prEN 10025-3:2011) has been prepared by Technical Committee ECISS/TC 103 “Structural steels other than reinforcements”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document will supersede EN 10025-3:2004.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of the EU Construction Products Directive (89/106/EEC). For relationship with the EU Construction Products Directive, see informative Annex ZA of prEN 10025-1:2010.

The titles of the other parts of this document are:

Part 1: General technical delivery conditions;

Part 2: Technical delivery conditions for non-alloy structural steels;

Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels;

Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance;

Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition.

1 Scope

Part 3 of this document, in addition to part 1, specifies requirements for flat and long products of hot rolled weldable fine grain structural steels in the normalized/normalized rolled delivery condition in the grades and qualities given in Tables 1 to 3 (chemical composition) and Tables 4 to 6 (mechanical properties) in thickness ≤ 250 mm.

In addition to prEN 10025-1:2010 the steels specified in this document are especially intended for use in heavily loaded parts of welded structures such as, bridges, flood gates, storages tanks, water supply tanks, etc., for service at ambient and low temperatures.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

2.1 General standards

- EN 1011-2, *Welding – Recommendations for welding of metallic materials - Part 2: Arc welding of ferritic steels.*
- EN 10020, *Definition and classification of grades of steel.*
- prEN 10025-1:2010, *Hot rolled products of structural steels - Part 1: General technical delivery conditions.*
- EN 10027-1, *Designation systems for steels - Part 1: Steel names.*
- EN 10027-2, *Designation systems for steels - Part 2: Numerical system.*
- EN 10163-1, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 1: General requirements.*
- EN 10163-2, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 2: Plates and wide flats.*
- EN 10163-3, *Delivery requirements for surface condition of hot-rolled steel plates, wide flats and sections – Part 3: Sections.*
- EN 10164, *Steel products with improved deformation properties perpendicular to the surface of the product - Technical delivery conditions.*
- EN 10221, *Surface quality classes for hot-rolled round bars and rods - Technical delivery conditions.*
- EN ISO 14713-2, *Guidelines and recommendations for the protection against corrosion of iron and steel structures – Zinc coating – Part 2: Hot dip galvanizing (ISO 14713-2:2010).*

prEN 10025-3:2011 (E)**2.2 Standards on dimensions and tolerances (see 7.7.1)**

EN 10017, *Non-alloy steel rod for drawing and/or cold rolling – Dimensions and tolerances.*

EN 10024, *Hot rolled taper flange I sections - Tolerances on shape and dimensions.*

EN 10029, *Hot rolled steel plates 3 mm thick or above - Tolerances on dimensions, shape and mass.*

EN 10034, *Structural steel I and H sections - Tolerances on shape and dimensions.*

EN 10048, *Hot rolled narrow steel strip - Tolerances on dimensions and shape.*

EN 10051, *Continuously hot-rolled uncoated plate, sheet and strip of non-alloy and alloy steels - Tolerances on dimensions and shape.*

EN 10055, *Hot-rolled steel equal flange tees with radiused root and toes - Dimensions and tolerances on shape and dimensions.*

EN 10056-1, *Structural steel equal and unequal leg angles - Part 1: Dimensions.*

EN 10056-2, *Structural steel equal and unequal leg angles - Part 2: Tolerances on shape and dimensions.*

EN 10058, *Hot rolled flat steel bars for general purposes - Dimensions and tolerances on shape and dimensions.*

EN 10059, *Hot rolled square steel bars for general purposes - Dimensions and tolerances on shape and dimensions.*

EN 10060, *Hot rolled round steel bars - Dimensions and tolerances on shape and dimensions.*

EN 10061, *Hot rolled hexagon steel bars - Dimensions and tolerances on shape and dimensions.*

EN 10067, *Hot rolled bulb flats - Dimensions and tolerances on shape, dimensions and mass.*

EN 10162, *Cold rolled steel sections - Technical delivery conditions - Dimensional and cross-sectional tolerances.*

EN 10279, *Hot rolled steel channels - Tolerances on shape, dimensions and mass.*

2.3 Standards on testing

EN 10160, *Ultrasonic testing of steel flat product of thickness equal to or greater than 6 mm (reflection method).*

EN 10306, *Iron and steel - Ultrasonic testing of H beams with parallel flanges and IPE beams.*

EN 10308, *Non-destructive testing - Ultrasonic testing of steel bars.*

EN ISO 643, *Steels – Micrographic determination of the apparent grain size (ISO 643:2003).*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in prEN 10025-1:2010 and the following apply.

3.1 normalizing rolling

rolling process in which the final deformation is carried out in a certain temperature range leading to a material condition equivalent to that obtained after normalizing so that the specified values of the mechanical properties are retained even after normalizing

NOTE In international publications for both the normalizing rolling, as well as the thermomechanical rolling, the expression "controlled rolling" may be found. However in view of the different applicability of the products a distinction of the terms is necessary.

3.2 fine grained steels

steels with fine grain structure with an equivalent index of ferritic grain size ≥ 6 determined in accordance with EN ISO 643

4 Classification and designation

4.1 Classification

4.1.1 Main quality classes

The steel grade S275 specified in this document shall be classified as non-alloy quality steel and steel grade S355 shall be classified as alloy quality steel and the steel grades S420 and S460 specified in this document shall be classified as alloy special steels according to EN 10020.

4.1.2 Grades and qualities

This document specifies four steel grades S275, S355, S420 and S460.

All the steel grades may be supplied in the following qualities as specified at the time of the order:

- with specified minimum values of impact energy at temperatures not lower than -20 °C , designated as N;
- with specified minimum values of impact energy at temperatures not lower than -50 °C , designated as NL.

4.2 Designation

4.2.1 The designation shall be in accordance with prEN 10025-1.

NOTE For a list of corresponding former designations see Annex A, Table A.1.

4.2.2 The designation shall consist of:

- number of this document (prEN 10025-3);
- steel name or the steel number; the steel name consisting of:
 - symbol S (for structural steel);

Bestelformulier

NEN

Stuur naar:

NEN Standards Products & Services
t.a.v. afdeling Klantenservice
Antwoordnummer 10214
2600 WB Delft

NEN Standards Products & Services

Postbus 5059
2600 GB Delft

Vlinderweg 6
2623 AX Delft

T (015) 2 690 390
F (015) 2 690 271

www.nen.nl/normshop

Ja, ik bestel

__ ex. NEN-EN 10025-3:2011 Ontw. en Warmgewalste producten van constructiestaal - Deel 3: Technische leveringsvoorwaarden voor normaalgegloeid/normaliserend gewalst fijnkorrelig constructiestaal € 23.85

Wilt u deze norm in PDF-formaat? Deze bestelt u eenvoudig via www.nen.nl/normshop

Gratis e-mailnieuwsbrieven

Wilt u op de hoogte blijven van de laatste ontwikkelingen op het gebied van normen, normalisatie en regelgeving? Neem dan een gratis abonnement op een van onze e-mailnieuwsbrieven. www.nen.nl/nieuwsbrieven

Retourneren

Fax: (015) 2 690 271
E-mail: klantenservice@nen.nl
Post: NEN Standards Products & Services,
t.a.v. afdeling Klantenservice
Antwoordnummer 10214,
2600 WB Delft
(geen postzegel nodig).

Gegevens

Bedrijf / Instelling _____

T.a.v. _____ O M O V

E-mail _____

Klantnummer NEN _____

Uw ordernummer _____ BTW nummer _____

Postbus / Adres _____

Postcode _____ Plaats _____

Telefoon _____ Fax _____

Factuuradres (indien dit afwijkt van bovenstaand adres)

Postbus / Adres _____

Postcode _____ Plaats _____

Datum _____ Handtekening _____

Voorwaarden

- De prijzen zijn geldig tot 31 december 2016, tenzij anders aangegeven.
- Alle prijzen zijn excl. btw, verzend- en handelingskosten en onder voorbehoud bij o.m. ISO- en IEC-normen.
- Bestelt u via de normshop een pdf, dan betaalt u geen handeling en verzendkosten.
- Meer informatie: telefoon (015) 2 690 391, dagelijks van 8.30 tot 17.00 uur.
- Wijzigingen en typfouten in teksten en prijsinformatie voorbehouden.
- U kunt onze algemene voorwaarden terugvinden op: www.nen.nl/leveringsvoorwaarden.