

ICS 13.030.01

English Version

Characterization of waste - Kinetic testing for assessing acid generation potential of sulfidic waste from extractive industries

Caractérisation des déchets - Essais cinétiques pour la détermination du potentiel de génération d'acide des déchets sulfurés des industries extractives

Charakterisierung von Abfällen - Kinetische Prüfungen zur Bestimmung des Säurebildungspotentials von sulfidhaltigen Abfällen der mineralgewinnenden Industrie

This Technical Report was approved by CEN on 9 April 2012. It has been drawn up by the Technical Committee CEN/TC 292.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Copyright
Preview
cen

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction.....	5
1 Scope.....	7
2 Methods.....	7
2.1 General.....	7
2.2 Planning.....	7
2.3 Testing data.....	9
2.4 Humidity cell test.....	10
2.5 Other column tests.....	11
2.6 Lysimeter.....	12
2.7 Field test.....	12
2.7.1 General.....	12
2.7.2 Rainfall simulation tests.....	13
2.7.3 Long-term field tests.....	13
2.8 Key testing variables.....	13
2.8.1 General.....	13
2.8.2 Sample size and sample preparation.....	14
2.8.3 Temperature.....	15
2.8.4 Duration.....	15
2.8.5 Sample selection.....	15
2.9 Method summary.....	15
3 Interpretation and evaluation.....	17
3.1 General.....	17
3.2 Reaction rates.....	17
3.2.1 General.....	17
3.2.2 Sulfide oxidation rate, assessed by sulfate release.....	18
3.2.3 Sulfide oxidation rate, assessed by oxygen consumption.....	19
3.3 Leaching rates.....	20
3.4 Leaching result evaluation.....	21
3.5 Application to field conditions.....	22
3.5.1 General.....	22
3.5.2 Mineralogy/mineral chemistry.....	23
3.5.3 Particle size.....	23
3.5.4 Texture / hydraulic conditions.....	24
3.5.5 Air flow / oxygen exposure.....	24
3.5.6 Temperature.....	24
3.5.7 Microbes (inhibitors/enhancers).....	24
3.5.8 Test duration.....	25
3.6 Field test evaluations.....	25
3.6.1 General.....	25
3.6.2 Rainfall simulation tests.....	25
3.6.3 Long-term field tests.....	25
4 Recommendations.....	27
4.1 General.....	27
4.2 Assess if the material is going acidic or not.....	27
4.3 Define sulfide oxidation rate.....	27
4.4 Define acid consuming reaction rate.....	27
4.5 Assess when the material will go acidic.....	28
4.6 Estimate leaching rates and leachate quality.....	28
4.7 Evaluate closure options.....	28

Bibliography.....29

Preview
Copyright

Foreword

This document (CEN/TR 16363:2012) has been prepared by Technical Committee CEN/TC 292 "Characterization of waste", the secretariat of which is held by NEN.

The preparation of this document by CEN is based on a mandate by the European Commission (Mandate M/395), which assigned the development of standards on the characterization of waste from extractive industries.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

Copyright
Preview

Introduction

A specific feature of sulfide containing waste is the risk for acid/neutral drainage generation (A/NRD). Acid drainage occurs if the acid generation from sulfide oxidation exceeds the acid buffering from minerals in the waste while, in this context, neutral drainage occurs when neutralisation generation exceeds the acid generation.

Test methods for the determination of acid generation behaviour can be divided into static and kinetic tests. A static test is used for screening purposes. It is usually relatively fast to perform, but gives only indicative information based on total content of sulfur (or sulfides) and of readily available buffering minerals in the waste material. Kinetic tests give more detailed information on behaviour based on the determination of mineral reaction rates under specified conditions. A European Standard, EN 15875, has been established for the static testing, while this Technical Report gives guidance on how the kinetic testing may be performed and interpreted.

Kinetic testing has been required as part of permit processes for many new and operating mine sites. Many different test methods have been used over the last 20 to 30 years. These tests are commonly designed to avoid that the oxidation rate is limited due to the lack of oxygen or build-up of secondary minerals. Kinetic tests based on current standards and laboratory-scale standard practise (ASTM D5744 - 96:2001 and ASTM D5744 - 07:2007; Morin and Hutt, 1997; Lapakko, 2003) are not designed to evaluate short- and long-term drainage water quality. However, adjustments to the standard protocols can be done to produce indicative information about short-term drainage water quality. Together with modelling, this information can be used to predict/estimate long-term drainage water quality.

This Technical Report is a guidance document that discusses the main kinetic test methods that are used within the mining sector internationally, the applicability of the different tests and how to evaluate the results. Kinetic test results may provide valuable information, but it is important to understand their limitations. Sulfide oxidation in the field is controlled by many different factors that may be difficult to simulate within the laboratory. Some of these factors may in fact be unknown at the time of testing. The complexity of applying test results to field conditions may to some extent be balanced by long experience in evaluating such data.

The objective of this Technical Report is to support the management of waste from extractive industries by giving guidance on how to characterize the kinetically controlled process of acid drainage generation.

The target audience of the document includes all stakeholders concerned with the management of extractive waste including the extractive industry, authorities, regulators, consultants, and testing laboratories.

Document structure

This Technical Report is organized to provide the answers to the three main questions below.

What type of data will kinetic testing provide and what methods are available? After introducing the concepts of kinetic testing for assessing acid generation potential of sulfidic waste, this clause (Clause 2) describes what type of information these tests provide. This clause also reviews the different tests methods and the ability to meet the objectives set out for the different kinetic tests. Methods to evaluate both acid generating reactions and neutralizing reactions are described.

Clause 2 Methods

How can the data be interpreted? This clause (Clause 3) gives guidance on how results from kinetic tests can be applied. Included in this clause is guidance on how results from the tests may be used to calculate the bulk oxidation rate for the material; to evaluate the leaching rates for elements within the test system; and based on the results, to evaluate mineral reactions in the system. Kinetic test relevance for describing field scale processes is discussed.

Clause 3 Interpretation and evaluation

What method to select? The clause ends with recommendations on the selection of kinetic test design depending on objective(s).

*Clause 4
Recommendations*

Forbiede
Preview

1 Scope

This Technical Report describes the performance and evaluation of kinetic tests for sulfidic waste material that, according to previous testing (primarily acid base accounting), is likely to go acidic or when the result of such testing is inconclusive. This Technical Report also covers the issue of drainage from sulfidic material that is likely to be well buffered but that will produce a neutral drainage potentially affected by sulfide mineral oxidation.

This Technical Report will not include aspects of sampling and testing that are already covered in the overall guidance document for characterisation of extractive waste (CEN/TR 16376) or in the guidance document on sampling of wastes from extractive industries (CEN/TR 16365).

2 Methods

2.1 General

It is necessary to have a good understanding of the waste material before kinetic (mineral reaction rate) testing is performed. This together with well-defined objectives will aid in selecting the methods. This clause describes the planning of kinetic testing, key elements to analyse for, and the main methods used by the industry.

2.2 Planning

Figure 1 shows a flow chart of the different steps to consider when planning for kinetic testing. A number of the steps in the flow chart are not further discussed in this document. More details on topics related to sampling are found in CEN/TR 16365, e.g. supporting information, data quality, documentation and reporting are discussed in overall guidance document (CEN/TR 16376). Additional information that puts kinetic testing in a wider context may also be found in the overall guidance document.

Copyright
Preview




Figure 1 — General outline of the steps involved when performing kinetic testing for assessing acid/neutral generation potential of sulfidic waste from extractive industries

The only kinetic test method that has been standardized is the so-called humidity cell test (HCT) (ASTM D5744 - 96:2001, ASTM D5744 - 07:2007 and ASTM D5744-12; Sobek et al, 1978). This method has been used extensively in the mining sector. The method is designed to evaluate long-term acid generation potential and not to predict long term mineral reactions and mineral leaching in the actual tailings management facility (TMF) or waste rock dump, as pointed out by Sobek et al (1978) and re-emphasized by Lapakko et al (2003) and EIPPCB (2004).

Kinetic tests can be designed as small laboratory tests or large-scale field tests. During the exploration phase only smaller amounts of material are available and humidity cell test are the most common kinetic test used. The interpretation of the humidity cell test may help in defining feasible waste management options.

Most of the laboratory tests are run with relatively small amounts of crushed material (a few hundred grams to a few kilograms) with an optimal amount of oxygen available. The amount of rinse solution used is intended to be high enough to ensure removal of all reaction products, so that secondary precipitates do not limit reactions. However, at higher pH (> 4 to 5) iron oxides are likely to precipitate.

If the exploration project proceeds into mining, larger amounts of material will become available for testing. This may give the opportunity to design and run tests that are larger and/or more suited to site-specific conditions (column tests, lysimeter tests, field tests, etc.). These tests will give more reliable results for evaluating the long-term oxidation and leaching rates.

Kinetic testing may be performed several times through the lifetime of an extractive operation. It is common to establish field tests with extensive instrumentation at an early stage of operation. These field tests can be considered kinetic verification tests and will give valuable information for the final planning for closure.

In summary, the main kinetic tests designs used by extractive industries internationally are:

- humidity cell tests;
- column tests;
- lysimeter tests; and
- field tests.

The humidity cell has a standard protocol while the other methods are site specific and not standardized. In practise, also the humidity cell test that are being run are for or by the extractive industry commonly deviate from the standard design by introducing more site-specific aspects.

If the humidity cell protocols are followed, the reaction products are to be flushed out at cyclic intervals. Column experiments can, however, be designed to allow for build-up of secondary minerals by reducing the water amount for flushing. The column is likely to induce a concentration gradient along the length of the axis in the flow direction.

There are also other test methods that can be useful for testing certain processes and reaction rates under given conditions. The listed four most commonly used tests are described in the following sections complemented by a few additional tests that may be useful for evaluating reaction and leaching rates.

2.3 Testing data

The kinetic testing data to be obtained from the different tests will depend on the defined objective(s). The primary data commonly include pH, alkalinity, sulfate and weight of the sample. However, when analysing leachate samples, it is often beneficial for the understanding of the processes within the tested material to do a multi-element analysis. Kinetic testing requires collecting and analysing many samples over a long period of time (months to years). Only a few basic parameters are normally analysed on a regular basis. When there is a significant change in the basic parameters (e.g. pH and sulfate, see below), a full chemical analysis of the leachate may be performed to better understand the processes taking place and to provide input data for estimations/evaluations of drainage water quality.

The key parameters will commonly include:

- alkalinity;
- pH;
- sulfate;
- total dissolved solids;
- key metals (copper for copper mines, nickel for nickel mines, etc.); and
- element concentrations (anions and cations) in the leachate.

In order to understand the geochemical processes taking place within the tests columns information may also be needed on test conditions and on the tested material. Relevant information may include:

- flow rate of air and water;
- oxygen / carbon dioxide (during the test run, under sealed conditions);

Bestelformulier

Stuur naar:

NEN Standards Products & Services
t.a.v. afdeling Klantenservice
Antwoordnummer 10214
2600 WB Delft



NEN Standards Products & Services

Postbus 5059
2600 GB Delft

Vlinderweg 6
2623 AX Delft

T (015) 2 690 390
F (015) 2 690 271

www.nen.nl/normshop

Ja, ik bestel

___ ex. CEN/TR 16363:2012 en Karakterisering van afval - Kinetische testen voor de beoordeling van verzurings potentieel van sulfide houdend afval uit winningsindustrieën € 52.00

Wilt u deze norm in PDF-formaat? Deze bestelt u eenvoudig via www.nen.nl/normshop

Gratis e-mailnieuwsbrieven

Wilt u op de hoogte blijven van de laatste ontwikkelingen op het gebied van normen, normalisatie en regelgeving? Neem dan een gratis abonnement op een van onze e-mailnieuwsbrieven. www.nen.nl/nieuwsbrieven

Gegevens

Bedrijf / Instelling _____

T.a.v. _____ O M O V

E-mail _____

Klantnummer NEN _____

Uw ordernummer _____ BTW nummer _____

Postbus / Adres _____

Postcode _____ Plaats _____

Telefoon _____ Fax _____

Factuuradres (indien dit afwijkt van bovenstaand adres)

Postbus / Adres _____

Postcode _____ Plaats _____

Datum _____ Handtekening _____

Retourneren

Fax: 015 2 690 271

E-mail: klantenservice@nen.nl

Post: NEN Standards Products & Services,

t.a.v. afdeling Klantenservice
Antwoordnummer 10214,
2600 WB Delft

(geen postzegel nodig).

Voorwaarden

- De prijzen zijn geldig tot 31 december 2018, tenzij anders aangegeven.
- Alle prijzen zijn excl. btw, verzend- en handelingskosten en onder voorbehoud bij o.m. ISO- en IEC-normen.
- Bestelt u via de normshop een pdf, dan betaalt u geen handeling en verzendkosten.
- Meer informatie: telefoon 015 2 690 391, dagelijks van 8.30 tot 17.00 uur.
- Wijzigingen en typfouten in teksten en prijsinformatie voorbehouden.
- U kunt onze algemene voorwaarden terugvinden op: www.nen.nl/leveringsvoorwaarden.