

Nederlandse norm

# NEN-EN 10277

(en)

Producten van blank staal - Technische  
leveringsvoorwaarden

Blank steel products - Technical delivery  
conditions

Vervangt NEN-EN 10277-1:2008;  
NEN-EN 10277-2:2008;  
NEN-EN 10277-3:2008;  
NEN-EN 10277-4:2008;  
NEN-EN 10277-5:2008;  
NEN-EN 10277:2017 Ontw.

ICS 77.140.10; 77.140.60

juni 2018

Als Nederlandse norm is aanvaard:  
 - EN 10277:2018,IDT

Normcommissie 342070 'Metaal' algemeen



**THIS PUBLICATION IS COPYRIGHT/PROTECTED**

**DEZE PUBLICATIE IS AUTEURSRECHTELIJK BESCHERMD**

Apart from exceptions provided by the law, nothing from this publication may be duplicated and/or published by means of photocopy, microfilm, storage in computer files or otherwise, which also applies to full or partial processing, without the written consent of the Royal Netherlands Standardization Institute.

The Royal Netherlands Standardization Institute shall, with the exclusion of any other beneficiary, collect payments owed by third parties for duplication and/or act in and out of law, where this authority is not transferred or falls by right to the Reproduction Rights Foundation.

Auteursrecht voorbehouden. Behoudens uitzondering door de wet gesteld mag zonder schriftelijke toestemming van het Koninklijk Nederlands Normalisatie-instituut niets uit deze uitgave worden verveelvoudigd en/of openbaar gemaakt door middel van fotokopie, microfilm, opslag in computerbestanden of anderszins, hetgeen ook van toepassing is op gehele of gedeeltelijke bewerking.

Het Koninklijk Nederlands Normalisatie-instituut is met uitsluiting van ieder ander gerechtigd de door derden verschuldigde vergoedingen voor verveelvoudiging te innen en/of daartoe in en buiten rechte op te treden, voor zover deze bevoegdheid niet is overgedragen c.q. rechtens toekomt aan de Stichting Reprorecht.

Although the utmost care has been taken with this publication, errors and omissions cannot be entirely excluded. The Royal Netherlands Standardization Institute and/or the members of the committees therefore accept no liability, not even for direct or indirect damage, occurring due to or in relation with the application of publications issued by the Royal Netherlands Standardization Institute.

Hoewel bij deze uitgave de uiterste zorg is nagestreefd, kunnen fouten en onvolledigheden niet geheel worden uitgesloten. Het Koninklijk Nederlands Normalisatie-instituut en/of de leden van de commissies aanvaarden derhalve geen enkele aansprakelijkheid, ook niet voor directe of indirecte schade, ontstaan door of verband houdend met toepassing van door het Koninklijk Nederlands Normalisatie-instituut gepubliceerde uitgaven.



©2018 Koninklijk Nederlands Normalisatie-instituut  
 Postbus 5059, 2600 GB Delft  
 Telefoon (015) 2 690 390, Fax (015) 2 690 190

EUROPEAN STANDARD

**EN 10277**

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2018

ICS 77.140.10; 77.140.60

Supersedes EN 10277-1:2008, EN 10277-2:2008,  
EN 10277-3:2008, EN 10277-4:2008,  
EN 10277-5:2008

English Version

**Bright steel products - Technical delivery conditions**Produits en aciers transformés à froid - Conditions  
techniques de livraison

Blankstahlerzeugnisse - Technische Lieferbedingungen

This European Standard was approved by CEN on 20 February 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

## Contents

Page

European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions.....	5
4 Classification and designation.....	6
5 Information to be supplied by the purchaser.....	7
6 Manufacturing process.....	8
7 Requirements.....	8
8 Inspection.....	11
9 Test methods.....	12
10 Marking.....	13
Annex A (informative) Steel grades and chemical composition according to EN 10025-2, EN ISO 683-1, EN ISO 683-2, EN ISO 683-3 and EN ISO 683-4.....	38
Annex B (normative) Ruling sections for mechanical properties.....	44
B.1 Definition.....	44
B.2 Determination of the diameter of the equivalent ruling section.....	44
Annex C (normative) Supplementary or special requirements.....	47
C.1 Introduction.....	47
C.2 Mechanical properties of reference test pieces in the quenched and tempered condition.....	47
C.3 Fine grain steel.....	47
C.4 Non-destructive tests (NDT).....	47
C.5 Disposition of tolerances.....	47
C.6 Condition of bar ends.....	48
C.7 Product analysis.....	48
C.8 Reduction ratio and deformation ratio.....	48
C.9 Temporary corrosion protection.....	48
C.10 Special agreements for marking.....	48
Annex D (normative) Methods for evaluating straightness.....	49
D.1 Scope.....	49
D.2 Recommended method.....	49
D.3 Alternative method for round bars (effective for diameters $\geq 10$ mm).....	49
Annex E (informative) Designation of steels given in this standard and of comparable grades covered in various designation systems.....	50
Bibliography.....	53

## European foreword

This document (EN 10277:2018) has been prepared by Technical Committee ECISS/TC 105 "Steels for heat treatment, alloy steels, free-cutting steels and stainless steels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2018 and conflicting national standards shall be withdrawn at the latest by December 2018.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10277-1:2008 to EN 10277-5:2008.

The following changes have been made in comparison to the previous edition EN 10277-1:2008 to EN 10277-5:2008:

- a) the five parts of EN 10277-1 to EN 10277-5 were merged into one part;
- b) the dimensional requirements for bright steel products were added to this standard;
- c) for the steels for general engineering use, the steel grades E295GC, E355GC, C10, C15, C16 and C55 were deleted and the grades C25, C30 and C50 were added;
- d) for the free cutting steels, the grades 9S20, 17SMn20, 35SMn20 and 35SMnPb20 were added;
- e) for the case hardening steels, the grades 16MnCrB 5, 15NiCrS4, 15NiCr13 and 17NiCrMoS6-4 were deleted, the grades C10E, C15E, C16E, 16MnCr5, 20Cr4, 20CrS4, 20MnCr5, 24CrMo4, 24CrMoS4, 16NiCr4, 16NiCrS4, 20NiCrMo2-2, 17NiCrMo6-4, 17NiCrMoS6-4 and 18CrNiMo7-6 were added;
- f) for the steels for quenching and hardening, the grade 39NiCrMo3 was deleted, the grades C25E, C25R, C30E, C30R, 28Mn6, 36Mn6, 42Mn6, 34Cr4, 37Cr4, 37CrS4, 41Cr4, 25CrMo4, 34CrMo4, 34CrMoS4, 42CrMo4, 50CrMo4, 36CrNiMo4 and 30CrNiMo8 were added;
- g) the standard was editorially revised.

This standard is the result of the work on ISO 683-18. Since the bright stainless steel products are to be found in EN 10088-3 for European standardization, they are excluded here. In addition, this standard was adapted to include the European references and some further amendments were made.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

**EN 10277:2018 (E)****1 Scope**

This document specifies the technical delivery requirements for bright steel bars in the drawn, peeled/turned or ground condition and they are intended for mechanical purposes, for example for machine parts. The bright bars are subdivided into the following steel types:

- a) non-alloy general engineering steels;
- b) non-alloy free-cutting steels;
- c) non-alloy and alloy case-hardening steels;
- d) non-alloy and alloy steels for quenching and tempering.

This document lists the mechanical characteristics for products up to 100 mm in thickness. For larger dimensions, the manufacturer and purchaser agree on mechanical properties at the time of enquiry and order.

It does not cover cold rolled products and cut lengths produced from strip or sheet by cutting. Bright steel products of stainless steels are to be found in EN 10088-3.

In addition to this document, the general technical delivery requirements of EN 10021 are applicable.

**2 Normative references**

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10020, *Definition and classification of grades of steel*

EN 10021:2006, *General technical delivery conditions for steel products*

EN 10025-2, *Hot rolled products of structural steels - Part 2: Technical delivery conditions for non-alloy structural steels*

EN 10027-1, *Designation systems for steels - Part 1: Steel names*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system*

EN 10079, *Definition of steel products*

EN 10204, *Metallic products - Types of inspection documents*

EN 10247, *Micrographic examination of the non-metallic inclusion content of steels using standard pictures*

CEN/TR 10261, *Iron and steel - European standards for the determination of chemical composition*

EN ISO 148-1, *Metallic materials - Charpy pendulum impact test - Part 1: Test method (ISO 148-1)*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377)*

EN ISO 643, *Steels - Micrographic determination of the apparent grain size (ISO 643)*

EN ISO 683-1, *Heat-treatable steels, alloy steels and free-cutting steels - Part 1: Non-alloy steels for quenching and tempering (ISO 683-1)*

EN ISO 683-2, *Heat-treatable steels, alloy steels and free-cutting steels - Part 2: Alloy steels for quenching and tempering (ISO 683-2)*

EN ISO 683-3, *Heat-treatable steels, alloy steels and free-cutting steels - Part 3: Case-hardening steels (ISO 683-3)*

EN ISO 683-4, *Heat-treatable steels, alloy steels and free-cutting steels - Part 4: Free-cutting steels (ISO 683-4)*

EN ISO 3887, *Steels - Determination of the depth of decarburization (ISO 3887)*

EN ISO 4885, *Ferrous materials - Heat treatments - Vocabulary (ISO 4885)*

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1)*

EN ISO 6892-1, *Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1)*

EN ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition (ISO 14284)*

ISO 286-2, *Geometrical product specifications (GPS) - ISO code system for tolerances on linear sizes - Part 2: Tables of standard tolerance classes and limit deviations for holes and shafts*

ISO 4967, *Steel - Determination of content of non-metallic inclusions - Micrographic method using standard diagrams*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10020, EN 10027-1, EN 10027-2, EN 10079, EN ISO 377, EN ISO 4885, EN ISO 14284 and the following apply.

#### 3.1

##### **bright steel products**

drawn or peeled/turned bars with smoother surface quality and better dimensional accuracy in comparison to hot-rolled bars

#### 3.2

##### **drawn products**

products of various cross-sectional shapes obtained, after descaling, by cold drawing of hot-rolled bars or rod, on a drawing bench (cold formation without removing material)

Note 1 to entry: This operation gives the product special features with respect to shape, dimensional accuracy and surface finish. In addition the process causes cold working of the product, which can be eliminated by subsequent heat treatment. Products in lengths are delivered straightened.

#### 3.3

##### **peeled/turned products**

round bars produced by peeling or turning where the product can be further processed by straightening and polishing

Note 1 to entry: This operation gives the bar special features with respect to shape, dimensional accuracy and surface finish. The removal of metal is carried out in such a way that the bright product is generally free from rolling defects and surface decarburization


**EN 10277:2018 (E)****3.4****ground products**

drawn or peeled/turned round bars given an improved surface quality and dimensional accuracy by grinding or by grinding and polishing

**3.5****thickness**

nominal dimension of the product

Note 1 to entry: That means:

- 
- a) the diameter in the case of rounds;
  - b) the lateral length in the case of squares;
  - c) the width over flats in the case of hexagons;
  - d) the shorter lateral length in the case of flats (rectangular bars) and wide-flats.

For special sections, 'thickness' has to be defined at the time of enquiry and order

**3.6****ovality**

difference between the smallest and largest dimension measured across the pairs of opposing points at a common cross-section

**3.7****out-of shape**

any deviation for the nominal section profile

**3.8****ruling section**

section for which the specified mechanical properties shall apply

Note 1 to entry: Independent of the actual shape and dimensions of the cross-section of the product, the size of its ruling section is always given by a diameter. This corresponds to the diameter of an "equivalent round bar". That is a round bar which will show the same cooling rate as the actual ruling section of the product concerned at its position for taking the test pieces, when being cooled from austenitizing temperature.

**4 Classification and designation****4.1 Classification**

The classification of the relevant steel grades is allocated in accordance with EN 10020. The general engineering and the free cutting steels are quality steels. The steels for case hardening and for quenching and tempering are special steels.

**4.2 Designation**

For the steel grades covered by this document, the steel names and numbers given in the relevant tables are allocated in accordance with EN 10027-1 and EN 10027-2.



## 5 Information to be supplied by the purchaser

### 5.1 Mandatory information

The manufacturer shall obtain the following information from the purchaser at the time of enquiry and order:

- a) quantity (mass, number of bars) to be delivered;
- b) shape of the product (e.g. round, hexagon, square, flat);
- c) the dimensions and tolerances of the product, see 7.7 and Tables 2 and 11 to 13;
- d) reference to this European Standard, i.e. EN 10277;
- e) the designation of the steel grade and the delivery condition (see Tables 4 to 10);
- f) standard designation for a test report 2.2 or, if required, any other type of inspection document in accordance with EN 10204.

### 5.2 Options/Supplementary or special requirements

A number of options are specified in this European standard and listed below. If the purchaser does not indicate the wish to implement any of these options, the products will be supplied in accordance with the basic specifications of this standard (see 5.1).

- a) Reference testing for products used in the quenched and tempered condition (for steels for quenching and tempering only, see Table 1, footnote d and C.2);
- b) any fine grain requirement and verification of fine grain size (see 7.3 and C.3);
- c) non-destructive testing (see 7.5 and C.4);
- d) the disposition of tolerances in accordance with 7.7 and C.5;
- e) bar end conditions may be specified at the time of enquiry and order in accordance with C.6;
- f) product analysis (see 7.1.2, Table 16 and C.7);
- g) for a minimum reduction ratio or minimum thickness deformation (see 6.1 and C.8)
- h) temporary corrosion protection (see 6.2.1 and C.9);
- i) any requirement to special marking (see Clauses 10 and C.10)
- j) any additional requirement concerning the surface condition, i.e. ground surface +G or polished surface +PL for round bars (see 6.2.2 and Table 2);
- k) surface quality class if another than the standard class is requested (see 7.8 and Table 3);
- l) verification of the straightness (see 7.7, Table 14 and Annex D);
- m) any requirement to the hardenability (+H, +HH, +HL), for special steels only (see 7.1.4);
- n) any requirement for non-metallic inclusions (see 7.4);
- o) any requirement regarding the permissible depth of decarburization (see 7.6);
- p) impact test at a temperature lower than room temperature (see 9.2.2).

**EN 10277:2018 (E)****5.3 Ordering examples**

## EXAMPLE

2 t round bars with nominal diameter 20 mm, tolerance h9, stock length 6 000 mm made of steel grade C45 according to this standard in delivery condition +C, surface quality class 1 and a test report 2.2 as specified in EN 10204.

**2 t round bars 20 h9 × stock 6000**

**steel grade EN 10277 —C45+C**

**Inspection document EN 10204 — 2.2**

**6 Manufacturing process****6.1 General**

The manufacturing process of the steel and of the products is with the restrictions given by the requirements in 6.2 and 6.3 left to the discretion of the manufacturer.

For minimum reduction ratio or minimum thickness deformation ratio of rolled and forged products, see C.8.

**6.2 Treatment and surface condition at delivery****6.2.1 Treatment condition**

The treatment and heat-treatment condition (if any) at the time of delivery must comply with the condition agreed in the order and shall be one of the conditions indicated in Table 1.

Bright steel products in cold drawn or peeled/turned condition are coated with a light film of grease from processing, for bright steel products in a finally heat-treated condition the manufacturer chooses the rust protection after heat treatment.

The usual light application of ordinary grease or oil does not afford positive protection against rusting, particularly in the presence of condensation water. The use of a selected rust inhibitor or a special type of packing shall, if required, be agreed at the time of enquiry and order, see C.9.

**6.2.2 Particular surface conditions**

Table 2 shows the possible surface conditions and tolerance classes according to ISO 286-2 at delivery.

**6.3 Traceability of the cast**

Each product shall be traceable to the cast, see Clause 10.

**7 Requirements****7.1 Chemical composition, mechanical properties and hardenability****7.1.1 General**

Combination of usual treatment conditions at the time of delivery and requirements concerning chemical composition and mechanical properties are shown in Tables 1.

### 7.1.2 Chemical composition

The chemical composition of the steels determined by the cast analysis, shall comply to EN 10025-2, EN ISO 683-1, EN ISO 683-2, EN ISO 683-3 and EN ISO 683-4. The grades and the chemical composition of the steels are listed for information in Annex A for EN 10025-2, EN ISO 683-1, EN ISO 683-2, EN ISO 683-3 and EN ISO 683-4.

Permissible deviations between the limiting values for cast analysis and the values for product analysis are given in the corresponding tables of EN 10025-2, EN ISO 683-1, EN ISO 683-2, EN ISO 683-3 and EN ISO 683-4. The product analysis shall be carried out when specified at the time of enquiry and order (see C.7).

If steels for case hardening or for quenching and tempering are ordered with hardenability requirements according to EN ISO 683-1, EN ISO 683-2 and EN ISO 683-3, such hardenability requirements shall be considered as the governing criteria for acceptance. In such cases, the cast analysis may deviate by the values given in EN ISO 683-1, EN ISO 683-2 and EN ISO 683-3, Table 3, footnote b.

**WARNING** Due to hazardous effects to health and environmental problems of Pb, it is recommended to use instead steels only with sulphur and other innocuous free-cutting element additions.

### 7.1.3 Mechanical properties

For steels ordered in one of the treatment conditions in Tables 1 and 2, the requirements for mechanical properties specified in Tables 4 to 10 apply. The mechanical property values given in Tables 4 to 10 apply to test pieces which have been taken and prepared in accordance with Figure 1.

In this case, the normal and narrowed hardenability values given in EN ISO 683-1, EN ISO 683-2 for special steels and the narrowed hardenability values in EN ISO 683-3 for alloy special steels are for guidance purposes only.

NOTE In Tables 4 to 10, grades alloyed with further elements for better machinability are not explicitly mentioned, but the mechanical properties are also valid for them (see Tables A.1 to A.4).

#### 7.1.4 Hardenability

Unless otherwise agreed for alloy case-hardening steels, the hardenability requirements given in EN ISO 683-3, Table 5 apply. If agreed at the time of enquiry and order, alloy case-hardening steels with restricted hardenability scatterbands given in EN ISO 683-3, Table 6 shall be supplied and these values apply in addition to Table 1, columns 6 and 7.

If special steels for quenching and tempering are ordered by using the designations to normal or to narrowed hardenability scatterbands, the values of hardenability given in EN ISO 683-1 or EN ISO 683-2 apply in addition to Table 1, columns 8 and 9.

NOTE In Tables 8 to 10, grades alloyed with further elements for better machinability are not explicitly mentioned, but the mechanical properties are also valid for them (see Tables A.3 and A.4).

### 7.2 Machinability

All steels are machinable in the conditions 'soft annealed' (+A) and treated to ferrite/pearlite structure (+FP).

Where improved machinability is required the grades with defined ranges of alloying elements, which support the machinability and/or with a specific treatment to improve machinability should be ordered (see also footnote b in Tables A.1, A.3 and A.4).

**EN 10277:2018 (E)**

Free-cutting steels with low carbon content have their best machinability in the cold drawn condition.

NOTE Non-leaded steels with comparable chemical composition generally have identical mechanical properties but often lower machinability than leaded steels.

**7.3 Grain size**

Unless otherwise agreed at the time of enquiry and order the grain size of the general engineering, free-cutting steels and the non-alloy steels for quenching and tempering shall be left to the discretion of the manufacturer. If a fine grain structure is required for non-alloy steels for quenching and tempering or for case-hardening or quenched and tempered free-cutting steels, Annex C, Option C.3 shall be ordered.

If direct hardening treatment is used for free-cutting case-hardening steels, a fine grain structure should be ordered.

The case-hardening and the alloy steels for quenching and tempering shall have a fine grain structure with an austenite grain size of 5 or finer, when tested in accordance with EN ISO 643. Only for verification see C.3.

**7.4 Non-metallic inclusions****7.4.1 Microscopic inclusions**

The special steels shall have a certain degree of cleanness, however, verification of the non-metallic inclusion content requires a special agreement. If there is such an agreement at the time of enquiry and order the microscopical non-metallic inclusion content shall be determined to an agreed procedure and within agreed limits (see ISO 4967 or EN 10247).

For grades with specified minimum sulphur content, the agreement should only concern the oxides.

**7.4.2 Macroscopic inclusions**

Freedom of macroscopic inclusions cannot be ensured in any steel. This requirement is applicable for the verification of the macroscopic inclusions in special steels. If verification is agreed then the method and acceptance limits shall be agreed at the time of enquiry and order.

**7.5 Internal soundness**

Where appropriate, requirements relating to the internal soundness of the products shall be agreed at the time of enquiry and order (see C.4).

**7.6 Decarburization**

For steels for quenching and tempering, requirements relating to the permissible depth of decarburization may be agreed at the time of enquiry and order.

The depth of decarburization shall be determined in accordance with the micrographic method specified in EN ISO 3887.

**7.7 Shape, dimensions and tolerances**

The tolerance class on thickness (and width for flats) shall comply with the requirements agreed at the time of enquiry and order and shall be in accordance with Table 2. If there is no agreement on the tolerance class the bright products are delivered with the standard tolerance class given in Table 2. The tolerance class and the corresponding tolerances are given in Table 11 for rounds, squares and hexagons and in Table 12 for drawn flats. Where specified by the purchaser at the time of enquiry and order the disposition tolerances specified in Table 11 shall be in accordance with C.5.

Unless otherwise agreed at the time of enquiry and order, the length and the tolerance on length shall be as specified in Table 13.

# ALTIJD DE ACTUELE NORM IN UW BEZIT HEBBEN?

Nooit meer zoeken in de systemen en uzelf de vraag stellen:  
'Is NEN-EN 10277:2018 en de laatste versie?'

Via het digitale platform NEN Connect heeft u altijd toegang tot de meest actuele versie van deze norm. Vervallen versies blijven ook beschikbaar. **U en uw collega's** kunnen de norm via NEN Connect makkelijk raadplagen, online en offline.

Kies voor slimmer werken en bekijk onze mogelijkheden op [www.nenconnect.nl](http://www.nenconnect.nl).

## Heeft u vragen?

Onze Klantenservice is bereikbaar maandag tot en met vrijdag, van 8.30 tot 17.00 uur.

Telefoon: 015 2 690 391

E-mail: [klantenservice@nen.nl](mailto:klantenservice@nen.nl)

