

norm**NEN-EN 10210-2**

Warmvervaardigde buisprofielen voor constructiedoeleinden - Deel 3: Toleranties, afmetingen en profieigenschappen

Publicatie uitsluitend voor commentaar

Hot finished steel structural hollow sections - Part 2: Tolerances, dimensions and sectional properties

augustus 2018
ICS 77.140.75

Commentaar vóór 2018-10-02

Vervangt NEN-EN 10210-3:2016 Ontw. Zal vervangen NEN-EN 10210-2:2006; NEN-EN 10210-2:2006/C1:2007

Als Europees normontwerp is gepubliceerd: prEN 10210-2:2018, IDT

Definitief vastgestelde normen zullen als Nederlandse norm gelden. Daarom wordt dit normontwerp in Nederland voor commentaar gepubliceerd. Op het ontwerp ingebracht commentaar zal aan de bevoegde normcommissie worden voorgelegd die hiermee rekening zal houden bij de bepaling van de Nederlandse stem. Indien er geen bezwaar bij NEN wordt gebracht, kan dat leiden tot ongewijzigde definitieve vaststelling van het ontwerp als norm.

Van Europese normen bestaan drie officiële versies: Engels, Frans en Duits. Voor Nederland zal de Engelse versie gelden. Daarnaast kan er gekozen worden voor een andere geautoriseerde versie in het Nederlands.

Normcommissie 342081 'Constructiestaal'



THIS PUBLICATION IS COPYRIGHT PROTECTED

DEZE PUBLICATIE IS AUTEURSRECHTELIJK BESCHERMD

Apart from exceptions provided by the law, nothing from this publication may be duplicated and/or published by means of photocopy, microfilm, storage in computer files or otherwise, which also applies to full or partial processing, without the written consent of the Royal Netherlands Standardization Institute.

The Royal Netherlands Standardization Institute shall, with the exclusion of any other beneficiary, collect payments owed by third parties for duplication and/or act in and out of law, where this authority is not transferred or falls by right to the Reproduction Rights Foundation.

Auteursrecht voorbehouden. Behoudens uitzondering door de wet gesteld mag zonder schriftelijke toestemming van het Koninklijk Nederlands Normalisatie-instituut niets uit deze uitgave worden verveelvoudigd en/of openbaar gemaakt door middel van fotokopie, microfilm, opslag in computerbestanden of anderszins, hetgeen ook van toepassing is op gehele of gedeeltelijke bewerking.

Het Koninklijk Nederlands Normalisatie-instituut is met uitsluiting van ieder ander gerechtigd de door derden verschuldigde vergoedingen voor verveelvoudiging te innen en/of daartoe in en buiten rechte op te treden, voor zover deze bevoegdheid niet is overgedragen c.q. rechtens toekomt aan de Stichting Reprorecht.

Although the utmost care has been taken with this publication, errors and omissions cannot be entirely excluded. The Royal Netherlands Standardization Institute and/or the members of the committees therefore accept no liability, not even for direct or indirect damage, occurring due to or in relation with the application of publications issued by the Royal Netherlands Standardization Institute.

Hoewel bij deze uitgave de uiterste zorg is nagestreefd, kunnen fouten en onvolledigheden niet geheel worden uitgesloten. Het Koninklijk Nederlands Normalisatie-instituut en/of de leden van de commissies aanvaarden derhalve geen enkele aansprakelijkheid, ook niet voor directe of indirecte schade, ontstaan door of verband houdend met toepassing van door het Koninklijk Nederlands Normalisatie-instituut gepubliceerde uitgaven.

Voorbeeld
Preview

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 10210-2

August 2018

ICS 77.140.75

Will supersede EN 10210-2:2006

English Version

Hot finished steel structural hollow sections - Part 2: Tolerances, dimensions and sectional properties

Profils creux de construction finis à chaud en aciers -
Partie 2 : Tolérances, dimensions et caractéristiques du
profil

Warmgefertigte Hohlprofile für den Stahlbau - Teil 3:
Grenzabmaße, Maße und statische Werte

This draft European Standard is submitted to CEN members for second enquiry. It has been drawn up by the Technical Committee ECISS/TC 103.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions.....	4
4 Symbols.....	4
5 Information to be obtained by the manufacturer.....	6
6 Tolerances.....	6
7 Measurement of size and shape.....	8
8 Dimensions and sectional properties.....	13
Annex A (normative) Formulae for the calculation of sectional properties.....	14
A.1 General.....	14
A.2 Circular hollow sections.....	14
A.3 Rectangular, including square, hollow sections.....	15
A.4 Elliptical hollow sections.....	17
Annex B (normative) Sectional properties for a limited range of standard sizes.....	19

Preview
 NEN-EN 10210-2

European foreword

This document (prEN 10210-2:2018) has been prepared by Technical Committee ECISS/TC 103 “Structural steels other than reinforcements”, the secretariat of which is held by DIN.

This document is currently submitted to the second CEN Enquiry.

This document will supersede EN 10210-2:2006.

This standard consists of the following parts:

- EN 103xx, *Steel structural hollow sections — General (Characteristics, evaluation of conformity and marking)* – in preparation
- EN 10210-1, *Hot finished steel structural hollow sections — Part 1: Technical delivery conditions*
- EN 10210-2, *Hot finished steel structural hollow sections — Part 2: Tolerances, dimensions and sectional properties*

It forms part of a series of standards on hollow sections together with EN 10219-1 and EN 10219-2.

Preview
prEN 10210-2

prEN 10210-2:2018 (E)**1 Scope**

This part of this European standard specifies tolerances for hot finished circular, square, rectangular and elliptical structural hollow sections, manufactured in wall thicknesses up to 120 mm, in the following size ranges:

- Circular: Outside diameters up to 2 500 mm;
- Square: Outside dimensions up to 800 mm × 800 mm;
- Rectangular: Outside dimensions up to 750 mm × 500 mm;
- Elliptical: Outside dimensions up to 500 mm × 250 mm.

The formulae for calculating sectional properties of sections manufactured to the dimensional tolerances of this standard, to be used for the purposes of structural design, are given in Annex A.

Dimensions and sectional properties for a limited range covering the more common sizes are given in Annex B.

NOTE The designation of the sections' major axis (yy) and its minor axis (zz) align with the axis designation used for structural design in the structural Eurocodes.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10210-1:2006, *Hot finished structural hollow sections of non-alloy and fine grain steels — Part 1: Technical delivery conditions*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10210-1 apply.

4 Symbols

For the purposes of this document, the symbols defined in Table 1 apply.

Table 1 — Symbols and definitions

Symbol	Unit	Definition
A	cm ²	Cross-sectional area
A_m	mm ²	Area of the surface delimited by the perimeter at mid-thickness
A_s	m ² /m	Superficial area per metre length
B	mm	Specified side dimension of a square hollow section. Specified dimension of the shorter side of a rectangular hollow section. Specified outside dimension of an elliptical section on its minor axis
C_1/C_2	mm	Length of corner region of a square or rectangular hollow section

Symbol	Unit	Definition
C_t	cm ³	Torsional modulus constant
D	mm	Specified outside diameter of a circular hollow section
D_{max}/D_{min}	mm	The maximum and minimum outside diameter of a circular hollow section measured in the same plane
e	mm	Deviation from straightness
H	mm	Specified dimension of the longer side of a rectangular hollow section. Specified outside dimension of an elliptical section on its major axis
I	cm ⁴	Second moment of area
I_t	cm ⁴	Torsional inertia constant (polar moment of inertia in the case of circular hollow sections only)
i	cm	Radius of gyration
L	mm	Length
M	kg/m	Mass per unit length
O	%	Out-of-roundness
P	mm	External perimeter of an elliptical hollow section
R	mm	External corner radius of a square or rectangular hollow section
T	mm	Specified thickness
U	mm	Perimeter of an elliptical hollow section at mid-thickness
V	mm	Total measured twist
V_1	mm	Twist measured at one end of a section
W_{el}	cm ³	Elastic section modulus
W_{pl}	cm ³	Plastic section modulus
x_1	mm	Concavity of a side of a square or rectangular hollow section
x_2	mm	Convexity of a side of a square or rectangular hollow section
yy	—	Axis of cross-section, major axis of a rectangular hollow section
zz	—	Axis of cross-section, minor axis of a rectangular hollow section
θ	°	Angle between adjacent sides of a square or rectangular hollow section

prEN 10210-2:2018 (E)**5 Information to be obtained by the manufacturer****5.1 Mandatory information**

The following mandatory information from this part of EN 10210 shall be obtained by the manufacturer at the time of enquiry and order:

- a) the dimensions (see Clause 8);
- b) the type of length, length range or length (see Table 3).

NOTE This information is included in the list of information to be obtained by the manufacturer contained in EN 10210-1:2006, Clause 5.

5.2 Options

Options are specified in this part of EN 10210. In the event that the purchaser does not indicate a wish to implement one of these options at the time of enquiry and order, the manufacturer shall supply in accordance with the basic specification.

- Option 2.1 The tolerance on approximate length shall be $^{+150}_0$ mm (see Table 3).
- Option 2.2 Tolerance of external corner radius of 2T maximum at each corner.
- Option 2.3 Out-of-roundness tolerances for diameter to thickness ratio exceeding 100 (see Table 2, footnote d).

6 Tolerances

6.1 Tolerances shall not exceed the values given in Table 2 for shape, straightness and mass, Table 3 for manufacturer's delivered length and Table 4 for the height of the internal and external weld bead of submerged arc welded hollow sections.

6.2 The internal corners of square and rectangular hollow sections shall be rounded, except in the case of EW sections for a corner containing the weld, should the weld be located in the corner region.

NOTE The internal corner profile is not specified.

Table 2 — Tolerances on shape, straightness and mass

Characteristic	Circular sections	hollow	Square rectangular sections	and hollow	Elliptical sections	hollow
Outside dimensions (D , B , H)	$\pm 1\%$ with a minimum of $\pm 0,5$ mm and a maximum of ± 10 mm		$\pm 1^a\%$ with a minimum of $\pm 0,5$ mm			
Thickness (T)	- 10 % ^{b c}					
Out-of-roundness (O)	2 % for hollow sections having a diameter to thickness ratio not exceeding 100 ^d		—			
Concavity/Convexity (x_1 , x_2) ^e	—		1 %		—	
Squareness of side (θ)	—		$90^\circ \pm 1^\circ$		—	
External corner profile (C_1 , C_2 or R) ^f	—		3T maximum at each corner		—	
Twist (V)	2 mm ^a plus 0,5 mm/m length ^a					
Straightness (e)	0,2 ^a % of total length and 3 mm over any 1 m length					
Mass (M)	- 6 %/+ 8 % on individual delivered lengths					
<p>^a For elliptical hollow sections of sizes $H < 250$ mm, the permitted tolerance is twice the value given in this table.</p> <p>^b The positive deviation is limited by the tolerance on mass.</p> <p>^c For seamless sections thicknesses of less than 10 % but not less than 12,5 % of the nominal thickness may occur in smooth transition areas over not more than 25 % of the circumference.</p> <p>^d When the diameter to thickness ratio exceeds 100, application of tolerance on out-of-roundness is not required, unless specifically agreed (see 5.2).</p> <p>^e The tolerance on convexity and concavity is independent of the tolerance on outside dimensions.</p> <p>^f The sides need not be tangential to the corner arcs.</p>						

ALTIJD DE ACTUELE NORM IN UW BEZIT HEBBEN?

Nooit meer zoeken in de systemen en uzelf de vraag stellen:
'Is NEN-EN 10210-2:2018 2e Ontw. en de laatste versie?'

Via het digitale platform NEN Connect heeft u altijd toegang tot de meest actuele versie van deze norm. Vervallen versies blijven ook beschikbaar. **U en uw collega's** kunnen de norm via NEN Connect makkelijk raadplagen, online en offline.

Kies voor slimmer werken en bekijk onze mogelijkheden op www.nenconnect.nl.

Heeft u vragen?

Onze Klantenservice is bereikbaar maandag tot en met vrijdag, van 8.30 tot 17.00 uur.

Telefoon: 015 2 690 391

E-mail: klantenservice@nen.nl

