



Nederlandse norm

NEN-EN 14215

(en)

Tapijten - Classificatie van machinaal vervaardigde pooltapijten en lopers

Textile floor coverings - Classification of machine-made rugs and runners

Vervangt NEN-EN 14215:2013;
NEN-EN 14215:2017 Ontw.

ICS 97.150
oktober 2018

Als Nederlandse norm is aanvaard:
 - EN 14215:2018,IDT

Voorbeeld
 Preview

Normcommissie 330024 'Tapijt'



THIS PUBLICATION IS COPYRIGHT/PROTECTED

DEZE PUBLICATIE IS AUTEURSRECHTELIJK BESCHERMD

Apart from exceptions provided by the law, nothing from this publication may be duplicated and/or published by means of photocopy, microfilm, storage in computer files or otherwise, which also applies to full or partial processing, without the written consent of the Royal Netherlands Standardization Institute.

The Royal Netherlands Standardization Institute shall, with the exclusion of any other beneficiary, collect payments owed by third parties for duplication and/or act in and out of law, where this authority is not transferred or falls by right to the Reproduction Rights Foundation.

Auteursrecht voorbehouden. Behoudens uitzondering door de wet gesteld mag zonder schriftelijke toestemming van het Koninklijk Nederlands Normalisatie-instituut niets uit deze uitgave worden verveelvoudigd en/of openbaar gemaakt door middel van fotokopie, microfilm, opslag in computerbestanden of anderszins, hetgeen ook van toepassing is op gehele of gedeeltelijke bewerking.

Het Koninklijk Nederlands Normalisatie-instituut is met uitsluiting van ieder ander gerechtigd de door derden verschuldigde vergoedingen voor verveelvoudiging te innen en/of daartoe in en buiten rechte op te treden, voor zover deze bevoegdheid niet is overgedragen c.q. rechtens toekomt aan de Stichting Reprorecht.

Although the utmost care has been taken with this publication, errors and omissions cannot be entirely excluded. The Royal Netherlands Standardization Institute and/or the members of the committees therefore accept no liability, not even for direct or indirect damage, occurring due to or in relation with the application of publications issued by the Royal Netherlands Standardization Institute.

Hoewel bij deze uitgave de uiterste zorg is nagestreefd, kunnen fouten en onvolledigheden niet geheel worden uitgesloten. Het Koninklijk Nederlands Normalisatie-instituut en/of de leden van de commissies aanvaarden derhalve geen enkele aansprakelijkheid, ook niet voor directe of indirecte schade, ontstaan door of verband houdend met toepassing van door het Koninklijk Nederlands Normalisatie-instituut gepubliceerde uitgaven.



©2018 Koninklijk Nederlands Normalisatie-instituut
 Postbus 5059, 2600 GB Delft
 Telefoon (015) 2 690 390, Fax (015) 2 690 190

EUROPEAN STANDARD

EN 14215

NORME EUROPÉENNE

EUROPÄISCHE NORM

October 2018

ICS 97.150

Supersedes EN 14215:2013

English Version

Textile floor coverings - Classification of machine-made rugs and runners

Revêtements de sol textiles - Classification des
carpettes et passages à velours manufacturés

Textile Bodenbeläge - Klassifizierung von
maschinengefertigten Teppichen und Läufern

This European Standard was approved by CEN on 17 June 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Identification requirements	5
5 Basic requirements	6
6 Classification for level of use intensity	6
7 Luxury classification	7
8 Additional characteristics	7
8.1 General	7
8.2 Castor chair suitability for occasional use	7
8.3 Suitability for use on stairs (runners only)	7
9 Report	7
Annex A (normative) Method to determine the calculated surface pile density	8
Annex B (normative) Criteria for the assessment of stair suitability	9
Annex C (normative) Summary test report	12
Annex D (normative) Lists of references	13

Preview
 NEN-EN 14215:2018

European foreword

This document (EN 14215:2018) has been prepared by Technical Committee CEN/TC 134 "Resilient, textile and laminate floor coverings", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2019, and conflicting national standards shall be withdrawn at the latest by April 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14215:2013.

In comparison with the previous edition, the following technical modifications have been made:

- the title has been corrected removing the word 'pile';
- 3 normative references have been updated.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 14215:2018 (E)**1 Scope**

This European Standard specifies requirements for machine-made (woven, tufted, knitted, needled, flocked, bonded, hand-tufted) rugs and runners, including a classification according to use intensity and luxury.

This European Standard is not applicable to hand-knotted rugs, to barrier mats or to bathroom rugs.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 985, *Textile floor coverings — Castor chair test*

EN 14159, *Textile floor coverings — Requirements for tolerances on (linear) dimensions of rugs, runners, carpet tiles and wall-to-wall carpet and for tolerances on pattern repeat*

EN ISO 105-B02, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test (ISO 105-B02)*

EN ISO 105-E01, *Textiles — Tests for colour fastness — Part E01: Colour fastness to water (ISO 105-E01)*

EN ISO 105-X12, *Textiles — Tests for colour fastness — Part X12: Colour fastness to rubbing (ISO 105-X12)*

EN ISO 9405, *Textile floor coverings — Assessment of changes in appearance (ISO 9405)*

EN ISO 12951, *Textile floor coverings — Determination of mass loss, fibre bind and stair nosing appearance change using the Lissontrotträd machine (ISO 12951)*

ISO 1763, *Carpets — Determination of number of tufts and/or loops per unit length and per unit area*

ISO 1765, *Machine-made textile floor coverings — Determination of thickness*

ISO 1766, *Textile floor coverings -- Determination of thickness of pile above the substrate*

ISO 2424:2007, *Textile floor coverings — Vocabulary*

ISO 4919, *Carpets — Determination of tuft withdrawal force*

ISO 8543, *Textile floor coverings — Methods for determination of mass*

ISO 10361, *Textile floor coverings — Production of changes in appearance by means of Vettermann drum and hexapod tumbler tester*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2424:2007 and the following apply.

3.1**SPT**

thickness of pile above the substrate in mm

3.2**SPW**

mass of pile per unit area above the substrate in g/m^2

3.3**SPD**

surface pile density in g/cm^3

3.4**SPD_c**

calculated surface pile density

3.5**N_z**

number of tufts/loops per dm^2

3.6**FD**

fibre density factor

4 Identification requirements

This clause specifies the requirements for the identification of the product and tolerances for the identifying properties.

The manufacturer of machine made rugs and runners shall provide information on the following in accordance with the terms and definitions according to ISO 2424:

- commercial reference,
- type of production technique,
- type of use surface,
- type of secondary backing (if applicable),

and shall declare the values of the characteristics listed in Table 1 using the test methods specified therein. The tolerances of the characteristics shall be in accordance with Table 1.

Table 1 — Identification requirements

Characteristics	Test method	Tolerances
Fibre composition of use-surface	Regulation EU N° 1007/2011	
Dimensions	EN 14159	EN 14159
Total thickness mm	ISO 1765	±10 %
Total mass per unit area g/m^2	ISO 8543	±10 %
If applicable: Mass of pile per unit area above the substrate (SPW) g/m^2	ISO 8543	±10 %
If applicable: Number of tufts/loops per unit area (N _z)	ISO 1763	±10 %
If applicable: Surface pile density (SPD) in g/cm^3	ISO 8543	±10 %

5 Basic requirements

The general properties of machine-made rugs and runners shall be in accordance with Table 2 when tested in accordance with the test methods therein.

Table 2 — Basic requirements

Characteristics	Requirements	Test methods
Colour fastness to light -man-made fibres -natural fibres	≥ 5 ≥ 4	EN ISO 105-B02
Colour fastness to rubbing - dry - wet	≥ 3 - 4 ≥ 3	EN ISO 105-X12
Colour fastness to Water (change in colour) - plain rugs and runners - patterned and with tonal effect Water (staining) - all rugs and runners	≥ 3 - 4 ≥ 4 ≥ 2 - 3 ^a	EN ISO 105-E01
Tuft withdrawal force: cut pile rugs ^b	3,0 N (average, with no individual result below 1,5 N)	ISO 4919
Tuft withdrawal force: loop pile rugs ^b	10,0 N (average, with no individual result below 5,0 N)	ISO 4919
Fibre bind (synthetic loop rugs and runners without pile only)	fuzzing, hairiness below level of reference photographs	EN ISO 12951, test C (200 cycles)
^a On multi fibre: worst result. ^b A representative number or tufts/loops shall be sampled, taking into account the binding.		

6 Classification for level of use intensity

Machine-made rugs and runners shall be classified for level of use intensity in accordance with the requirements of Table 3 (for all classes). For pile rugs and runners classified as class 23, SPD_c (g/cm³) shall be minimum 0,12 and SPW (g/m²) shall be minimum 1 500 g/m². Annex A defines the method to determine the calculated surface pile density.

The change in appearance is determined in accordance with ISO 10361 in either the Hexapod or the Vettermann apparatus using the number of cycles for long term tests. The tested specimens shall be assessed in accordance with EN ISO 9405 and the median grade for overall change in appearance shall meet the requirements specified in Table 3.

Table 3 — Classification for use intensity - Change in appearance - Requirements

Class	Vettermann (20 000 cycles) or Hexapod (12 000 cycles) (ISO 10361)
	Change of appearance rating (EN ISO 9405)
21	2
22	3
23	4

7 Luxury classification

Machine-made rugs and runners without pile shall be classified as LC1.

Machine-made pile rugs and runners shall be classified as specified in Table 4.

Table 4 — Luxury class by mass of pile per unit area above the substrate

Luxury class	SPW (in g/m ²) According to ISO 8543
LC1	< 600
LC2	≥ 600
LC3	≥ 800
LC4	≥ 1 000
LC5	≥ 1 500

8 Additional characteristics

8.1 General

The following additional claims may be made for products described in this document.

8.2 Castor chair suitability for occasional use

If a claim for castor chair suitability for occasional use is made, the product shall meet the requirement for an occasional use $r \geq 2,0$ when tested according to EN 985, Test A.

8.3 Suitability for use on stairs (runners only)

The product shall meet the requirement specified in Annex B when tested to EN ISO 12951.

9 Report

The results taken from the test reports of the individual test required for classification shall be summarized as shown in Annex C.

ALTIJD DE ACTUELE NORM IN UW BEZIT HEBBEN?

Nooit meer zoeken in de systemen en uzelf de vraag stellen:
'Is NEN-EN 14215:2018 en de laatste versie?'

Via het digitale platform NEN Connect heeft u altijd toegang tot de meest actuele versie van deze norm. Vervallen versies blijven ook beschikbaar. **U en uw collega's** kunnen de norm via NEN Connect makkelijk raadplagen, online en offline.

Kies voor slimmer werken en bekijk onze mogelijkheden op www.nenconnect.nl.

Heeft u vragen?

Onze Klantenservice is bereikbaar maandag tot en met vrijdag, van 8.30 tot 17.00 uur.

Telefoon: 015 2 690 391

E-mail: klantenservice@nen.nl

