

Nederlandse norm

# NEN-EN 13454-2

(en)

Bindmiddelen en fabrieksmatig vervaardigde  
mengsels voor dekvloeren van calciumsulfaat -  
Deel 2: Beproevingmethoden

Binders for floor screeds based on calcium  
sulphate - Part 2: Test methods

Vervangt NEN-EN 13454-2:2004+A1:2007;  
NEN-EN 13454-2:2017 Ontw.

ICS 91.100.10; 91.100.50

januari 2019

Als Nederlandse norm is aanvaard:  
 - EN 13454-2:2019, IDT

Preview  
 Copyright ©

Normcommissie 353099 'Verzameling geregistreerde onderwerpen'



**THIS PUBLICATION IS COPYRIGHT PROTECTED**

**DEZE PUBLICATIE IS AUTEURSRECHTELIJK BESCHERMD**

Apart from exceptions provided by the law, nothing from this publication may be duplicated and/or published by means of photocopy, microfilm, storage in computer files or otherwise, which also applies to full or partial processing, without the written consent of the Royal Netherlands Standardization Institute.

The Royal Netherlands Standardization Institute shall, with the exclusion of any other beneficiary, collect payments owed by third parties for duplication and/or act in and out of law, where this authority is not transferred or falls by right to the Reproduction Rights Foundation.

Auteursrecht voorbehouden. Behoudens uitzondering door de wet gesteld mag zonder schriftelijke toestemming van het Koninklijk Nederlands Normalisatie-instituut niets uit deze uitgave worden verveelvoudigd en/of openbaar gemaakt door middel van fotokopie, microfilm, opslag in computerbestanden of anderszins, hetgeen ook van toepassing is op gehele of gedeeltelijke bewerking.

Het Koninklijk Nederlands Normalisatie-instituut is met uitsluiting van ieder ander gerechtigd de door derden verschuldigde vergoedingen voor verveelvoudiging te innen en/of daartoe in en buiten rechte op te treden, voor zover deze bevoegdheid niet is overgedragen c.q. rechtens toekomt aan de Stichting Reprorecht.

Although the utmost care has been taken with this publication, errors and omissions cannot be entirely excluded. The Royal Netherlands Standardization Institute and/or the members of the committees therefore accept no liability, not even for direct or indirect damage, occurring due to or in relation with the application of publications issued by the Royal Netherlands Standardization Institute.

Hoewel bij deze uitgave de uiterste zorg is nagestreefd, kunnen fouten en onvolledigheden niet geheel worden uitgesloten. Het Koninklijk Nederlands Normalisatie-instituut en/of de leden van de commissies aanvaarden derhalve geen enkele aansprakelijkheid, ook niet voor directe of indirecte schade, ontstaan door of verband houdend met toepassing van door het Koninklijk Nederlands Normalisatie-instituut gepubliceerde uitgaven.



©2019 Koninklijk Nederlands Normalisatie-instituut  
 Postbus 5059, 2600 GB Delft  
 Telefoon (015) 2 690 390, Fax (015) 2 690 190

EUROPEAN STANDARD

**EN 13454-2**

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2019

ICS 91.100.10; 91.100.50

Supersedes EN 13454-2:2003+A1:2007

English Version

## Binders for floor screeds based on calcium sulphate - Part 2: Test methods

Liants à base de sulfate de calcium pour chapes - Partie  
2 : Méthodes d'essai

Calciumsulfat-Binder für Estriche - Teil 2:  
Prüfverfahren

This European Standard was approved by CEN on 19 November 2018.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels**

**Contents**

Page

European foreword.....	3
1 Scope.....	4
2 Normative references.....	4
3 Terms and definitions.....	4
4 Test conditions and sampling.....	4
4.1 General requirements for testing.....	4
4.2 Sampling for binders.....	5
5 Test methods for binders.....	5
5.1 Content of calcium sulphate.....	5
5.2 Determination of pH-value.....	6
5.3 Determination of setting time.....	7
5.4 Determination of mechanical resistance.....	12
5.5 Determination of shrinkage and swelling.....	17
5.6 Determination of working time.....	20
6 Test report.....	21
Bibliography.....	22

Preview  
 Copyright

## European foreword

This document (EN 13454-2:2019) has been prepared by Technical Committee CEN/TC 241 "Gypsum and gypsum based products", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2019, and conflicting national standards shall be withdrawn at the latest by July 2019.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document will supersede EN 13454-2:2003+A1:2007.

The main differences between this document and EN 13454-2:2003+A1:2007 are:

- a) the title was adapted;
- b) the normative references were updated;
- c) the terms 'flow diameter' and 'spread' were interchanged;
- d) the clause on sampling for factory made mixtures was deleted;
- e) a differentiation between binders for stiff and flowing mixtures was introduced;
- f) the setting time for binders for flowing mixtures was introduced;
- g) the final setting time was deleted;
- h) the working time for binders and factory made mixtures were introduced;
- i) the test methods for factory made mixtures (CA) were deleted;
- j) the document was editorially revised.

EN 13454, *Binders for floor screeds based on calcium sulphate* consists of two parts:

- *Part 1: Definitions and requirements*
- *Part 2: Test methods*

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

## 1 Scope

This document describes the test methods for binders for floor screeds based on calcium sulphate specified in EN 13454-1. In addition, some of the described test methods apply for factory made mixtures for floor screeds based on calcium sulphate specified in EN 13813.

This document describes reference test methods. If methods and conditions other than these are used, it is important to show that they give results equivalent to those given by the reference methods. In the event of a dispute, only the reference test method is used.

This document describes test methods for binders and made mixtures where the principal active component is calcium sulphate.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 196-1:2016, *Methods of testing cement - Part 1: Determination of strength*

EN 196-3:2016, *Methods of testing cement - Part 3: Determination of setting times and soundness*

EN 196-7, *Methods of testing cement - Part 7: Methods of taking and preparing samples of cement*

EN 459-2:2010, *Building lime - Part 2: Test methods*

EN 13279-2, *Gypsum binders and gypsum plasters - Part 2: Test methods*

EN 13454-1, *Binders for floor screeds based on calcium sulphate - Definitions and requirements*

EN 13813, *Screed material and floor screeds - Screed material - Properties and requirements*

EN 13892-1, *Methods of test for screed materials - Part 1: Sampling making and curing specimens for test*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Test conditions and sampling

### 4.1 General requirements for testing

#### 4.1.1 Water

The water used for testing and chemical analyses shall be distilled or deionized.

Unless otherwise specified, the water temperature shall be the same as the air temperature in the laboratory.

#### 4.1.2 Apparatus

The apparatus used for gauging and the moulds used for preparing the test specimens shall be free from leaks and shall be manufactured from a water proof material which is non-reactive to calcium sulphate (e.g. glass, brass, stainless steel, hardened steel, hard rubber and plastics, etc.).

Since the characteristics of calcium sulphate are strongly influenced by the presence of particles of calcium sulphate dihydrate which can influence the setting time, all equipment used in the tests shall be kept in a perfect state of cleanliness.

#### 4.2 Sampling for binders

Sampling for binders shall be carried out in accordance with EN 196-7 and EN 459-2.

### 5 Test methods for binders

#### 5.1 Content of calcium sulphate

##### 5.1.1 Principle

The calcium sulphate is decomposed by digestion with hydrochloric acid solution. Insoluble impurities are removed by filtration. The sulphate in the filtrate is determined gravimetrically as barium sulphate.

##### 5.1.2 Apparatus

- a) Sieve 0,1 mm mesh.
- b) 600 ml and 800 ml beakers.
- c) Rapid filtration funnels.
- d) Muffle furnace.
- e) Ignition crucible, porosity.
- f) Filter paper capable of retaining particles greater than 2,5  $\mu\text{m}$ .
- g) Porous porcelain or silica crucible.

##### 5.1.3 Reagents

- a) Hydrochloric acid solution: 2 N;
- b) Ammonia solution: (50 % by volume)
- c) Barium chloride: (3 % by mass solution in water)
- d) Methyl orange or other suitable indicator.

##### 5.1.4 Procedure

Grind the dried sample until it passes completely through a sieve with a mesh of 0,1 mm. Weigh accurately about 0,5 g into a 600 ml beaker, add 25 ml of hot distilled water.

Mix the sample and water with a glass rod until all the lumps are dispersed. Add 25 ml of 2 N HCl. Bring to boil and maintain this for 10 min. Add 150 ml of hot water and allow boiling for 15 min. Remove the beaker from the heat and filter through the filter paper into an 800 ml beaker. Wash out the beaker and filter paper using hot distilled or deionized water until the filtrate is free of chloride.

**EN 13454-2:2019 (E)**

Make up to approximately 350 ml using distilled water. Add a few drops of indicator and neutralize with ammonia solution. Add 20 ml 2 N HCl. Bring to boil again and add 50 ml of hot barium chloride solution stirring vigorously during the addition. Bring to boil and allow to settle just below boiling for at least 30 min.

Filter by one of the following methods:

a) Filtration using filter crucibles.

Ignite a clean ignition crucible, porosity 4, or a porous porcelain filter crucible at  $(800 \pm 25)^\circ\text{C}$  for 10 min.

Cool in a desiccator to room temperature and weigh.

Decant the clear liquid through the crucible using a slight suction. Wash the precipitate 3 times by decantation with hot water, transfer to the crucible and wash 6 times with small quantities of hot water. The last wash should be chloride free. Dry the crucible and contents and ignite at  $(800 \pm 25)^\circ\text{C}$  for 10 min.

b) Filtration using filter paper.

Use filter paper as described. Decant the clear liquid through the filter paper. Wash the precipitate 3 times by decantation with hot water, transfer to the filter paper and wash with small quantities of hot water until the wash is chloride free.

After filtration and washing fold the paper around the precipitate and place it in a weighed porcelain or silica crucible, previously ignited at  $(800 \pm 25)^\circ\text{C}$  and cooled in a desiccator. Heat gently to char the paper and expel the volatile matter. Do not allow the paper to burst into flames. Raise the temperature slowly to burn off the carbon with free access of air.

Finally ignite for 10 min at  $(800 \pm 25)^\circ\text{C}$ . Cool in a desiccator and weigh. Calculate the  $\text{CaSO}_4$  content as a percentage from the formula:

$$[\text{CaSO}_4] = W_2 \times 58,33 / W_1 \quad (1)$$

where

$W_1$  is the mass of sample, in grams;

$W_2$  is the mass of precipitate, in grams.

## 5.2 Determination of pH-value

Disperse 1 part by mass of the pulverized sample in 10 parts by mass of deionized or distilled water. Stir it for 5 min and then measure the pH-value by a pH-meter or pH-paper to the nearest  $\pm 0,5$  pH.



## 5.3 Determination of setting time

### 5.3.1 Determination of CAB and CAC setting time

#### 5.3.1.1 Principle

Determine setting time using the method given in EN 196-3, "binder" being substituted, where "cement" is mentioned.

The setting time is determined by observing the penetration of a needle into a binder paste of standard consistency according to EN 196-3:2016, Clause 5 until it reaches a specified value.

Binder paste of standard consistency has a specified resistance to penetration by a standard plunger. The water required for such a paste is determined by trial penetrations of pastes with different water contents.

#### 5.3.1.2 Apparatus

- a) Mixer: As described in EN 196-1:2016, 4.4.
- b) Vicat penetration apparatus: As described in EN 196-3:2016, 5.1.

#### 5.3.1.3 Standard consistency test

Use the Vicat apparatus as shown in Figure 1 a) with the plunger shown in Figure 1 b). The plunger (Figure 1 b)) shall be of non-corrodible metal in the form of a right cylinder of  $(50 \pm 1)$  mm effective length and of  $(10,00 \pm 0,05)$  mm diameter. The total mass of moving parts shall be  $(300 \pm 1)$  g. Their movement shall be truly vertical and without appreciable friction, and their axis shall coincide with that of the plunger.

The Vicat mould (see Figure 1 a)) to contain the paste under test shall be of hard rubber. It shall be of truncated conical form  $(40,0 \pm 0,2)$  mm deep and shall have internal diameters at top of  $(70 \pm 5)$  mm and at bottom of  $(80 \pm 5)$  mm. It shall be adequately rigid and shall be provided with a plane glass base-plate larger than the mould and at least 2,5 mm thick.

NOTE Moulds of metal or plastic or of cylindrical form can be used provided that they are of the specified depth and that they can be shown to give the same test results as the specified hard rubber mould of truncated conical form.

# ALTIJD DE ACTUELE NORM IN UW BEZIT HEBBEN?

Nooit meer zoeken in de systemen en uzelf de vraag stellen:  
'Is NEN-EN 13454-2:2019 en de laatste versie?'

Via het digitale platform NEN Connect heeft u altijd toegang tot de meest actuele versie van deze norm. Vervallen versies blijven ook beschikbaar. **U en uw collega's** kunnen de norm via NEN Connect makkelijk raadplagen, online en offline.

Kies voor slimmer werken en bekijk onze mogelijkheden op [www.nenconnect.nl](http://www.nenconnect.nl).

## Heeft u vragen?

Onze Klantenservice is bereikbaar maandag tot en met vrijdag, van 8.30 tot 17.00 uur.

Telefoon: 015 2 690 391

E-mail: [klantenservice@nen.nl](mailto:klantenservice@nen.nl)

