

Vervangt NEN-EN 14771:2003 Ontw.

Nederlandse norm

NEN-EN 14771 (en)

Bitumen en bitumineuze bindmiddelen -
Bepaling van de buigkruipstijfheid - Buigproef
Rheometer (BBR)

Bitumen and bituminous binders - Determination of the
flexural creep stiffness - Bending Beam Rheometer (BBR)

ICS 75.140; 91.100.50

mei 2005

Als Nederlandse norm is aanvaard:
 - EN 14771:2005, IDT

VOORBEELD
 Preview

Normcommissie 353 008 "Bitumen"

Apart from exceptions provided by the law, nothing from this publication may be duplicated and/or published by means of photocopy, microfilm, storage in computer files or otherwise, which also applies to full or partial processing, without the written consent of the Netherlands Standardization Institute.

The Netherlands Standardization Institute shall, with the exclusion of any other beneficiary, collect payments owed by third parties for duplication and/or act in and out of law, where this authority is not transferred or falls by right to the Reproduction Rights Foundation.

Auteursrecht voorbehouden. Behoudens uitzondering door de wet gesteld mag zonder schriftelijke toestemming van het Nederlands Normalisatie-instituut niets uit deze uitgave worden verveelvoudigd en/of openbaar gemaakt door middel van fotokopie, microfilm, opslag in computerbestanden of anderszins, hetgeen ook van toepassing is op gehele of gedeeltelijke bewerking.

Het Nederlands Normalisatie-instituut is met uitsluiting van ieder ander gerechtigd de door derden verschuldigde vergoedingen voor verveelvoudiging te innen en/of daartoe in en buiten rechte op te treden, voor zover deze bevoegdheid niet is overgedragen c.q. rechtens toekomt aan de Stichting Reprorecht.

Although the utmost care has been taken with this publication, errors and omissions cannot be entirely excluded. The Netherlands Standardization Institute and/or the members of the committees therefore accept no liability, not even for direct or indirect damage, occurring due to or in relation with the application of publications issued by the Netherlands Standardization Institute.

Hoewel bij deze uitgave de uiterste zorg is nagestreefd, kunnen fouten en onvolledigheden niet geheel worden uitgesloten. Het Nederlands Normalisatie-instituut en/of de leden van de commissies aanvaardden derhalve geen enkele aansprakelijkheid, ook niet voor directe of indirecte schade, ontstaan door of verband houdend met toepassing van door het Nederlands Normalisatie-instituut gepubliceerde uitgaven.

Nederlands voorwoord

Voor de in deze norm vermelde normatieve verwijzingen bestaan in Nederland de volgende equivalenten:

<u>vermelde norm</u>	<u>Nederlandse norm</u>	<u>titel</u>
EN 58	NEN-EN 58	Bitumen en bitumineuze bindmiddelen - Monsterneming van bitumineuze bindmiddelen (en)
EN 12594	NEN-EN 12594	Bitumen en bitumineuze bindmiddelen - Monstervoorbereiding (en)

Voorbereiding

Preview

ICS 75.140; 91.100.50

English version

Bitumen and bituminous binders - Determination of the flexural
creep stiffness - Bending Beam Rheometer (BBR)

Bitumes et liants bitumineux - Détermination du module de
rigidité en flexion - Rhéomètre à flexion du barreau (BBR)

Bitumen und bitumenhaltige Bindemittel - Bestimmung der
Biegekriechsteifigkeit - Biegebalkenrheometer (BBR)

This European Standard was approved by CEN on 25 March 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle.....	5
5 Apparatus	5
6 Preparation of test samples.....	6
7 Procedure	7
8 Calculation.....	8
9 Expression of results	9
10 Precision.....	9
11 Test report	10

Orbbee.nl
Preview

Foreword

This document (EN 14771:2005) has been prepared by Technical Committee CEN/TC 336 "Bituminous binders", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2005, and conflicting national standards shall be withdrawn at the latest by November 2005.

This European Standard is based on ASTM D 6648-01.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Orb
Preview
EEN

1 Scope

This European Standard specifies a method for the determination of the flexural creep stiffness of bituminous binders in the range of 30 MPa to 1 GPa by means of the bending beam rheometer.

WARNING — The use of this European Standard may involve hazardous materials, operations and equipment. This European Standard does not purport to address all of the safety problems associated with its use. It is the responsibility of the user of this European Standard to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 58, *Bitumen and bituminous binders – Sampling bituminous binders*

EN 12594, *Bitumen and bituminous binders – Preparation of test samples*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1 flexural creep stiffness

$S(t)$
ratio obtained by dividing the bending stress by the bending strain; the strain will increase with the loading time and therefore the flexural creep stiffness will also be a function of time

3.2 m-value

the absolute value of the slope of the curve of the logarithm of the stiffness versus the logarithm of time

3.3 contact load

P_c
load required to maintain positive contact between the test specimen, supports and the loading shaft

NOTE The contact load of 25 mN to 45 mN is used in this method.

3.4 test load

P_t
load used to determine the stiffness of the bituminous binder being tested

NOTE The test load of 930 mN to 1030 mN is used in this method.

4 Principle

The bending beam rheometer is used to measure the mid-point deflection, in three point bending, of a beam of bituminous binder. A constant load is applied to the mid-point of the test specimen for a defined loading time and the deflection is measured as a function of time. A low temperature liquid bath is used to control the temperature. The stiffness of the test specimen for the specific loading times is calculated from the bending stress and strain.

5 Apparatus

5.1 Bending Beam Rheometer (BBR), consisting of a loading frame with test specimen supports, a controlled temperature liquid bath and a data acquisition system.

5.1.1 The loading frame consists of a set of sample supports, a blunt-nosed shaft to apply the load to the mid-point of the test specimen, a load cell mounted in line with the loading shaft, a means for zeroing the load applied to the specimen, a means for applying a constant load to the test specimen and a deflection measuring transducer attached to the loading shaft. A schematic picture of the device is shown in Figure 1.

5.1.1.1 The loading system shall be capable of applying a contact load of 25 mN to 45 mN to the test specimen and maintaining a test load of 930 mN to 1030 mN within ± 10 mN. The rise time from the contact load to the test load shall be less than 0,5 s. Details of the loading pattern are shown in Figure 2.

5.1.1.2 The loading shaft shall be continuous and in line with the load cell and deflection measuring transducer with a spherically-shaped end $6,3 \text{ mm} \pm 0,3$ mm in radius.

5.1.1.3 The load cell shall have a minimum capacity of no less than 2,0 N and a resolution of at least 2,5 mN.

5.1.1.4 The LVD-transducer, or other suitable device to measure the deflection of the test specimen shall have a linear range of at least 6 mm, and be capable of resolving linear movement of $2,5 \mu\text{m}$.

5.1.1.5 The sample supports shall consist of two non-corrosive metal supports with a $3,0 \text{ mm} \pm 0,3$ mm contact radius and spaced 101 mm to 103 mm apart. The spacing of the supports shall be measured to 0,3 mm, see Figure 3.

5.1.2 A temperature measurement device, as a calibrated temperature transducer shall be capable of measuring the temperature with the accuracy of $\pm 0,1 \text{ }^\circ\text{C}$ over the range of $-36 \text{ }^\circ\text{C}$ to $0 \text{ }^\circ\text{C}$. The measuring head shall be mounted within 50 mm of the mid-point of the test specimen.

5.1.3 A liquid bath capable of maintaining the desired test temperature near the test sample within $\pm 0,2 \text{ }^\circ\text{C}$ during isothermal conditioning and during test procedure in the range of $-36 \text{ }^\circ\text{C}$ to $0 \text{ }^\circ\text{C}$. Bath liquid shall not affect the properties of the bituminous binder being tested. The density of the liquid shall not exceed 1050 kg/m^3 at the test temperature.

NOTE 95 % (volume fraction) ethanol has been found to be suitable as a bath liquid.

5.1.3.1 A bath agitator shall be used for maintaining the required temperature homogeneity with agitation intensity such that the fluid currents do not disturb the testing process.

5.1.3.2 A circulating bath, an optional separate bath unit, cools the test bath liquid.

5.1.4 A data acquisition and control system resolves loads to at least 2,5 mN, test specimen deflection to at least $2,5 \mu\text{m}$, and bath liquid temperature to the nearest $0,1 \text{ }^\circ\text{C}$. The software shall control the measuring system and record time, load deflection and temperature during the test. All the load and deflection readings shall be an average of at least five points within $\pm 0,2$ s of the reporting time.

Bestelformulier

NEN

Stuur naar:

NEN Standards Products & Services
t.a.v. afdeling Klantenservice
Antwoordnummer 10214
2600 WB Delft

NEN Standards Products & Services

Postbus 5059
2600 GB Delft

Vlinderweg 6
2623 AX Delft

T (015) 2 690 390
F (015) 2 690 271

www.nen.nl/normshop

Ja, ik bestel

__ ex. NEN-EN 14771:2005 en Bitumen en bitumineuze bindmiddelen - € 49.30
Bepaling van de buigkruipstijfheid - Buigproef Rheometer (BBR)

Wilt u deze norm in PDF-formaat? Deze bestelt u eenvoudig via www.nen.nl/normshop

Gratis e-mailnieuwsbrieven

Wilt u op de hoogte blijven van de laatste ontwikkelingen op het gebied van normen, normalisatie en regelgeving? Neem dan een gratis abonnement op een van onze e-mailnieuwsbrieven. www.nen.nl/nieuwsbrieven

Retourneren

Fax: (015) 2 690 271
E-mail: klantenservice@nen.nl
Post: NEN Standards Products & Services,
t.a.v. afdeling Klantenservice
Antwoordnummer 10214,
2600 WB Delft
(geen postzegel nodig).

Gegevens

Bedrijf / Instelling _____

T.a.v. _____ O M O V

E-mail _____

Klantnummer NEN _____

Uw ordernummer _____ BTW nummer _____

Postbus / Adres _____

Postcode _____ Plaats _____

Telefoon _____ Fax _____

Factuuradres (indien dit afwijkt van bovenstaand adres)

Postbus / Adres _____

Postcode _____ Plaats _____

Datum _____ Handtekening _____

Voorwaarden

- De prijzen zijn geldig tot 31 december 2016, tenzij anders aangegeven.
- Alle prijzen zijn excl. btw, verzend- en handelingskosten en onder voorbehoud bij o.m. ISO- en IEC-normen.
- Bestelt u via de normshop een pdf, dan betaalt u geen handeling en verzendkosten.
- Meer informatie: telefoon (015) 2 690 391, dagelijks van 8.30 tot 17.00 uur.
- Wijzigingen en typfouten in teksten en prijsinformatie voorbehouden.
- U kunt onze algemene voorwaarden terugvinden op: www.nen.nl/leveringsvoorwaarden.