



Tabel 1. Prestatieniveaus

Test	Level 1	Level 2	Level 3	Level 4	Level 5
6.1 Slijtvastheid (aantal wrijvingen)	100	500	2000	8000	-
6.2 Coupetest: Snijbestendigheid (index)	1,2	2,5	5,0	10,0	20,0
6.4 Scheurbestendigheid (N)	10	25	50	75	-
6.5 Prikbestendigheid (N)	20	60	100	150	-

Tabel 2. Prestatieniveaus voor materialen getest met EN-ISO 13997

Test	Level A	Level B	Level C	Level D	Level E	Level F
6.3 TDM: Snijbestendigheid (N)	2	5	10	15	22	30